


A. GÖMANN, J. A. DEVERELL, K. F. MUNTING, R. C. JONES, T. RODEMANN, A. J. CANTY, J. A. SMITH,* R. M. GUIJT* (UNIVERSITY OF TASMANIA, HOBART, AUSTRALIA)
 Palladium-Mediated Organic Synthesis Using Porous Polymer Monolith Formed in situ as a Continuous Catalyst Support Structure for Application in Microfluidic Devices
Tetrahedron **2009**, 65, 1450-1454.

Flow-Through Reaction in Palladium-Supported Microreactors



Significance: The authors reported the Sonogashira and the Suzuki–Miyaura reaction performed with microflow reactors filled with palladium polymer (Ø 250 μm, length 5 cm). Thus, the Sonogashira reaction of iodobenzene (**1a**) and phenylacetylene (**2**) was carried out with the microreactor **A** or **B** to give diphenylacetylene (**3**) in 96% (with **A**) or 95% yield (with **B**), respectively. The Suzuki–Miyaura reaction of aryl halides **1a–e** with 4-tolylboronic acid (**4**) gave the corresponding biphenyls **5a–e** under similar flow-reaction conditions in 11–97% yield.

Comment: Chloromethylstyrene (**6**) and divinylbenzene (**7**) were polymerized inside a capillary [pretreated with 3-(trimethoxysilyl)propyl methacrylate] in the presence of a porogen (toluene–dodecanol) and AIBN to afford a polymer-installed capillary **8**. The capillary **8** was subsequently treated with the ligand precursor [1-methylimidazole **9** (for **A**) or 5-amino-1,10-phenanthroline **10** (for **B**)] and PdCl₂(MeCN)₂ to give the reactive capillary **A** and **B**.

SYNFACTS Contributors: Yasuhiro Uozumi, Yoichi M. A. Yamada, Toshihiro Watanabe
 Synfacts 2009, 5, 0567-0567 Published online: 22.04.2009
 DOI: 10.1055/s-0029-1216548; Reg-No.: Y03009SF